PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT) (51) International Patent Classification 6: (11) International Publication Number: WO 98/50392 C07F 9/6568, 17/00, C08F 10/00 (43) International Publication Date: 12 November 1998 (12.11.98) (21) International Application Number: (74) Agents: CHISHOLM, P., Scott et al., Nova Chemicals Ltd., PCT/CA98/00428 2928 - 16 Street N.E., Calgary, Alberta T2E 7K7 (CA). (22) International Filing Date: 1 May 1998 (01.05.98) (81) Designated States: AL, AM, AT, AU, AZ, BA, BG, BR, BY, (30) Priority Data: CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU. 2,204,803 8 May 1997 (08.05.97) ID, IL, IP, KE, KG, KP, KR, KZ, LK, LT, LV, MX, NO, CA (71) Applicant (for all designated States except US): NOVA CHEM-ICALS (INTERNATIONAL) S.A. [CH/CH]; Route de la KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, Glane 107, P.O. Box 76, CH-1752 Villars-sur-Glane 1 CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, (CH). ML, MR, NE, SN, TD, TG). (72) Inventors; and (75) Inventors/Applicants (for US only): SPENCE, Rupert, Edward, von Haken [GB/CA]; 401 - 11 Street N.W., Calgary, Alberta Published T2N 1X5 (CA). GAO, Xiaoliang [CA/CA]; 6 Varmoor Place N.W., Calgary, Alberta T3A 0A1 (CA). KOCH, Linda [CA/CA]; 409, 5204 Dalton Drive N.W., Calgary, Alberta With international search report. T3A 3H1 (CA). BROWN, Stephen, John [CA/CA]; 157 Mount Sparrowhawk Place S.E., Calgary, Albena T2Z 2G7 (CA). HARRISON, Daryll, G. [CA/CA]; 619 Oaktidge Way S.W., Calgary, Alberta T2V 177 (CA). WANG, Qinyan [CN/CA]; Apartment 4, 1831 - 14 Avenue N.E., Calgary. Alberta T2E 1G7 (CA).

(54) Tide: PROCESS TO PREPARE BRIDGED PHOSPHOLE-CYCLOPENTADIENYL COMPOUNDS

(57) Abstract

A new family of phospholes having a metalloid bridge to a cyclopentadienyl group is prepared by reacting an organometallic cylcopentadienyl reagent with a "halogenated phosphole" (having a halogen or pseudohalogen group). The new phospholes may be used to prepare organometallic phospholyl complexes. Group 4 metal complexes of these phospholes are excellent polymerization catalysts,

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
ΛM	Amenia	FI	Finland	LT	Lithuania	SK	Slovatia
ΛT	Austria	ľR	France	w	Luxembourg	SN	Senegal
ΛU	Australia	CA	Gabon	LV	Latvia	SZ	Swaziland
AZ	A zerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
DA	Bosnia and Herzegovina	CB	Georgia	MD	Republic of Moldova	TC	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajitistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	
8C	Bulgaria	HU	Hungary	ML	Mali	11	Turkey
BJ	Benin	IB	Ireland	MN	Mongolia	UA	Trinidad and Tobago
BR	Brazil	IL	Israel	MR	Mauritania		Ukraine
BY	Belanus	IS	Ice land .	MW	Malawi	UG	Uganda
CA	Canada	IT	luly	MX	Mexico	US	United States of America
CF	Central African Republic	JP	Japan	NB.		UZ	Uzbekistan
CG	Congo	KB	Kenya		Niger	VN	Vict Nam
CII	Switzerland	KG	•	NL	Netherlands	YU	Yugoslavia
CI	Cae d'Ivoire	KP	Kyrgyzsian	NO	Notway	zw	Zimbabwe
CM	Cameroon	AF	Democratic People's	NZ.	New Zealand		
CN	China	l/n	Republic of Korea	PL	Poland		
Cυ	Cuba	KR	Republic of Korea	PT	Portugal		
cz		KZ.	Kazakstan	RO	Romania		
DB	Czech Republic	LC	Saint Lucis	RU	Russian Federation		
DK	Germany С	IJ	Liechtenstein	SD	Sudan		
UK	Denmark	LK ·	Sri Lanka	CD	Canadan		_

PROCESS TO PREPARE BRIDGED PHOSPHOLE-CYCLOPENTADIENYL COMPOUNDS

TECHNICAL FIELD

This invention relates to a new family of phospholes and a process to prepare these phospholes; to a process to use these phospholes to prepare a family of organometallic compounds having a cyclopentadienyl-type ligand which is bridged through a metalloid to a phospholyl ligand ("Cp-bridged-phosphole") and to a process to polymerize olefins using a Cp-bridged-phosphole.

BACKGROUND ART

Cyclopentadienyl-type ligands have been used to prepare organometallic complexes which, in turn, are useful in such applications as olefin polymerizations, alkene isomerizations and hydrogenations.

More recently, the use of phospholes to prepare phospholyl-type organometallic complexes has been disclosed.

The use of phospholyl-type complexes (and "mixed" cyclopentadienyl/phospholyl complexes - i.e. a complex having a cyclopentadienyl and a phospholyl-type ligand) is disclosed in U.S. patent 5,434,116 (Sone, to Tosoh), published European Patent Office (EPO) applications 617,052 (Aoki *et al*, to Asahi), and EPO 741,145 (Katayama *et al*, to Sumitomo) and Patent Cooperation Treaty (PCT) application 95/04087 (de Boer *et al*, to Shell).

It is also known to prepare "bridged and substituted" cyclopentadienyl-type ligands - as disclosed, for example, in U.S. patents 5,563,284; 5,565,396, and 5,554,795 (Frey *et al*), 5,324,800 (Welborn). These "bridged" cyclopentadienyls form catalyst systems for olefin polymerization when activated by a "substantially non-coordinating anion" (as disclosed by Hlatky and Tumer in U.S. patent 5,153,157 and 5,198,401) or an alumoxane.

20

30

.10

20

30

However, there is no known teaching of any process to prepare ligands having a cyclopentadiene-type group which is bridged to a phosphole.

DISCLOSURE OF THE INVENTION

An object of the present invention is to provide a new family of phospholes and a process to prepare the phospholes.

Another object of the invention is to use the new phospholes to prepare a family of new organometallic complexes having a bridged ligand with a metalloid "bridge" between a cyclopentadienyl group and a phospholyl group.

Another object of the invention is to provide processes for olefin polymerization using a catalyst system which includes these new organometallic complexes and an activator.

Thus, in one embodiment of the invention there is provided a phosphole characterized by having at least two substituents (a) and (b) where substituent (a) is a leaving group bonded to the phosphorus atom in the phosphole ring and substituent (b) is bonded to one carbon atom in the phosphole ring and is defined by the formula:

wherein Cp* is selected from cyclopentadienyl; substituted cyclopentadienyl; indenyl; substituted indenyl; fluorenyl and substituted fluorenyl; each SI is a non-interfering spectator ligand; Y is a metalloid bridging atom selected from Si, Ge, Sn, N, P, B and AI; and Z is one, two or three depending upon the valence of atom Y. For example, if Y is Si or Ge (which are four valent), then Z is 2. Similarly, if Y is three valent nitrogen, then Z is 1.

In another embodiment, this invention provides a process to prepare a phosphole as described above wherein the process comprises the reaction of a reactive organometallic cyclopentadienyl reagent with a halogenated phosphole defined by the formula:

20

30

wherein:

 $R_{1},\ R_{2},\ and\ R_{3},\ are\ hydrogen\ or\ non-interfering\ substituents;$

SI is a spectator ligand;

Y is Si, Ge, Sn, N, P, B and Al;

Z is one, two or three depending upon the valence of Y;


L is a leaving group; and

Hal is a halogen or pseudohalogen.

In another embodiment, the invention provides a process to prepare group 4 metal complexes of the above-described phospholes.

In another embodiment, the invention provides a process for polymerizing at least one polymerizable alpha olefin comprising reacting an activator and a group 4 organometallic complex of the present, inventive phospholes.

In a preferred embodiment, there is provided a high temperature olefin polymerization process using an activator and catalyst in which the catalyst is a group 4 organometallic complex defined by the formula:



wherein:

10

20

30

Flu* is selected from fluorenyl and substituted fluorenyl; each SI is a non-interfering spectator ligand;

Y is selected from Si, Ge, and Sn;

 $R_1,\,R_2,\,$ and R_3 are hydrogen or non-interfering substituents; M4 is selected from Ti, Zr and Hf; and

each X is an anionic ligand and n is 1 or 2 depending upon the oxidation state of M4.

BEST MODE FOR CARRYING OUT THE INVENTION

PART I: Novel Phospholes

The novel phospholes of the present invention are characterized by having (a) a substituent which is a leaving group (to facilitate further manipulations of the phosphole molecule); and (b) a substituent which includes a cyclopentadienyl structure and a metalloid bridge between the phosphole and the cyclopentadienyl structure.

A discussion of each of the features of these novel phospholes is provided below.

The term "phosphole" is meant to convey its conventional meaning, namely a cyclic dienyl structure having four carbon atoms and one phosphorus atom in the ring. The simplest phosphole is illustrated below:

It will be readily appreciated by those skilled in the art that the hydrogen atoms shown in the above formula may be replaced with other substituents.

The novel phospholes of this invention contain a cyclopentadienetype group. As used herein the term "cyclopentadiene-type" is meant to convey its conventional meaning and to include indene and fluorene ligands. The simplest (unsubstituted) cyclopentadiene, indene and fluorene structures are illustrated below.

cyclopentadiene

indene

fluorene

20

30

It will be readily appreciated by those skilled in the art that the hydrogen atoms shown in the above formula may be replaced with substituents to provide the "substituted" analogues. Thus, in the broadest sense, the inventive phospholes contain a cyclopentadienyl structure which may be an unsubstituted cyclopentadienyl, unsubstituted indenyl, substituted indenyl, unsubstituted fluorenyl or substituted fluorenyl. A description of permissible substituents on these cyclopentadienyl type structures is provided in the aforementioned Welborn '800 reference.

An illustrative list of such substituents for cyclopentadienyl groups includes C_1 - C_{20} hydrocarbyl radicals; substituted C_1 - C_{20} hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical or a radical containing a Lewis acidic or basic functionality; substituted C_1 - C_{20} hydrocarbyl radicals wherein the substituent contains an atom selected from the group 14 of the Periodic Table of Elements (where group 14 refers to IUPAC nomenclature); and halogen radicals, amido radicals, phosphido radicals, alkoxy radicals, alkyborido radicals, or a radical containing Lewis acidic or basic functionality; or a ring in which two adjacent R-groups are joined forming C_1 - C_{20} ring to give a saturated or unsaturated polycyclic ligand.

It should be further noted that the aforementioned Frey et al references teach cyclopentadienyl type ligands (including indenyl and fluorenyl) which may be substituted with phosphorus-containing substituents. By way of clarification, the phosphorus-containing substituents disclosed by Frey et al are not within a ring structure (i.e. Frey et al do not disclose phospholes but, rather, phosphido or phosphino substituted cyclopentadienyls).

The inventive phospholes contain a metalloid bridge between the phosphole ring and the cyclopentadienyl structure. The term "metalloid" as used herein is meant to refer to the group which includes silicon (Si); germanium (Ge); Tin (Sn); nitrogen (N); phosphorus (P); boron (B); and aluminum (Al). The "metalloid" is a "bridging" atom which is bonded to a

carbon atom in the phosphole ring and to the cyclopentadienyl group. The metalloid has additional valences which are filled with "spectator ligands (i.e. ligands which must be on the metalloid but which are not important to the substance of this invention). Illustrative examples of spectator ligands include hydrogen, halides, and hydrocarbyl ligands containing from 1 to 15 carbon atoms. For convenience, it is preferred that each of the spectator ligands is either a –CH₃ (methyl) fragment or phenyl fragment.

10

The preferred metalloids are Si, Ge, and Sn with Si being especially preferred. Thus, the preferred phospholes are illustrated by the formula:

20

wherein:

R₁, R₂, and R₃ are hydrogen or non-interfering substituents;

Y is Si, Ge or Sn;

SI is a spectator ligand;

L is a leaving group; and

Cp* is a cyclopentadienyl-type structure as described above.

30

As shown in the above formula, it is most preferred that the metalloid is bonded to a carbon atom adjacent to the phosphorus atom of the phosphole.

The (optional) "non-interfering" substituents on the phosphole (i.e. R_1 , R_2 , and R_3) generally encompass any substituent which doesn't interfere with further manipulation of the phosphole. An illustrative list of non-interfering substituents includes C_1 - C_{20} hydrocarbyl radicals; substituted C_1 - C_{20} hydrocarbyl radicals wherein one or more hydrogen

20

30

)

atoms is replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical or a radical containing a Lewis acidic or basic functionality; substituted C_1 - C_{20} hydrocarbyl radicals wherein the substituent contains an atom selected from the group 14 of the Periodic Table of Elements; and halogen radicals, amido radicals, phosphido radicals, alkoxy radicals, alkyborido radicals, or a radical containing Lewis acidic or basic functionality; or a ring in which two adjacent R-groups are joined forming C_1 - C_{20} ring to give a saturated or unsaturated polycyclic ligand.

The inventive phospholes are further characterized by having a "leaving group" bonded to the phosphorus atom in the ring.

As used herein, the term "leaving group" is intended to convey its conventional meaning to organometallic chemists - i.e. a fragment or group which may be cleaved off in a manner which facilitates further manipulation of the subject molecule. Examples of suitable leaving groups bonded to the phosphorus atom include a single H atom (which may, for example, be cleaved off with an alkyl lithium reagent), trialkyl (or triaryl) tin, trialkyl (or triaryl) Si; group 1 or group 2 atoms, or aryl, with aryl (especially phenyl) being preferred.

The inventive phospholes may be used to prepare organometallic complexes, such as Group 4 metal complexes having a dianonic ligand with a metalloid bridge, a phospholyl ligand group which is pi bonded to the metal and cyclopentadienyl-ligand group which is also pi bonded to the metal.

PART II: Process To Prepare The Phospholes

The preferred process to prepare the novel phospholes is by reacting an organometallic cyclopentadienyl reagent and a "bifunctional phosphole".

The organometallic cyclopentadienyl reagent is defined by the formula:

Cp*M

20

30

wherein Cp* is selected from unsubstituted cyclopentadienyl, substituted cyclopentadienyl, unsubstituted indenyl, substituted indenyl, unsubstituted fluorenyl, and substituted fluorenyl; and M is a group 1 or 2 metal (i.e. Li, Na, K, Rb, Cs, Be, Mg, Ca, Sr or Ba) or Al or Tl.

The "bifunctional phosphole" has (a) a leaving group bonded to the phosphorus atom and (b) a halogen or pseudohalogen containing group bonded to a carbon atom adjacent to the phosphorus atom. The preparation of such a bifunctional phosphole is described in the examples.

The term "leaving group" is used in the manner previously discussed (with the preferred leaving group being aryl, especially phenyl).

The term halogen is well known and the term pseudohalogen is also used conventionally - i.e. to identify (to a skilled organometallic chemist) a group which will behave similarly to a halogen in subsequent manipulations of the molecule. A common pseudohalogen is an -OR group (where the R is hydrogen or a hydrocarbyl fragment having from 1 to 20 carbon atoms).

The preferred group of organometallic reagents are Li salts of substituted fluorenyls.

The reaction preferably is undertaken in a solvent (or diluent) such as an ether, a $C_{5\cdot 20}$ alkane, an aromatic or mixture thereof at a temperature of from -100°C to 150°C (most preferably from -78°C to 25°C).

Part III: Preparation of Group 4 Organometallic Complexes

The preferred process to prepare the group 4 organometallic complexes is undertaken by reacting a group 4 metal (i.e. Ti, Hf or Zr) complex with a reagent derived from the novel phosphole complexes described in Part I above.

The group 4 metal is preferably in the highest oxidation state (though Ti(III) is also suitable) and is most preferably a tetrahalide (especially ZrCl₄).

The preferred initial step is to lithiate the phosphole. In some instances it may be possible to obtain the desired group 4 organometallic

complexes from a direct reaction between the lithiated phosphole and the metal halide. However, in other instances it may be necessary to prepare an intermediate reagent (for example, by reaction of the lithiated phosphole with trimethyl silicon chloride or trimethyl tin chloride, and then reacting this intermediate with the group 4 metal halide - as illustrated in the Examples). (Skilled organometallic chemists will recognize that the use of this intermediate involves extra time/expense but can improve the final yield of the group 4 organometallic complex.)

10

The reaction preferably is done in a solvent (or diluent) such as an ether, alkane, or aromatic. Toluene is the most preferred solvent,


The reaction temperature is preferably from -150°C to 250°C (most preferably from 20°C to 150°C).

The resulting group 4 organometallic complexes are defined by the following formula ("formula 1"):

20

30

ì



wherein:

 R_1 , R_2 , and R_3 are hydrogen or non-interfering substituents (as described in Part I above);

(SI)_z
I is a metalloid bridge having at least one spectator

Y — ligand (as described in Part 1 above);

Cp* is a cyclopentadienyl, indenyl or fluorenyl (each optionally substituted as described in Part 1 above);

M4 is a group 4 metal (i.e. Ti, Zr or Hf); and

X is a ligand or ligands bonded to the group 4 metal and n is 1 or 2 depending upon the oxidation state of M4.

20

30

By way of further explanation: If the group 4 metal is in oxidation state +3 and X is a simple anionic ligand then there will be only one X (and similarly, there will be two X ligands if the metal is 4+). X is, in general, a simple anionic ligand. Any such simple anionic ligand which may be bonded to an analogous metallocene complex should be acceptable in the present complexes. An illustrative list of such anionic ligands includes hydrogen, amidos, halogens and hydrocarbyls having up to 10 carbon atoms (with chlorine being preferred, for simplicity).

Part IV: Polymerization

The polymerization process of this invention is conducted in the presence of a catalyst which is an organometallic complex according to the aforedefined formula 1 and an "activator or cocatalyst". The terms "activator" or "cocatalyst" may be used interchangeably and refer to a catalyst component which combines with the organometallic complex to form a catalyst system that is active for olefin polymerization.

Preferred cocatalysts are the well known alumoxane (also known as aluminoxane) and ionic activators.

The term "alumoxane" refers to a well known article of commerce which is typically represented by the following formula:

R2'AIO(R'AIO)mAIR2'

where each R' is independently selected from alkyl, cycloalkyl, aryl or alkyl substituted aryl and has from 1-20 carbon atoms and where m is from 0 to about 50 (especially from 10 to 40). The preferred alumoxane is methylalumoxane or "MAO" (where each of the R' is methyl).

Alumoxanes are typically used in substantial molar excess compared to the amount of metal in the catalyst. Aluminum:transition metal molar ratios of from 10:1 to 10,000:1 are preferred, especially from 50:1 to 500:1.

As used herein, the term "ionic activator" is meant to refer to the well known cocatalyst systems described in the aforementioned Hlatky and Turner U.S. patent references, and the carbonium, sulfonium and oxonium analogues of such ionic activators which are disclosed by Ewen

in United States patent 5,387,568. In general, these ionic activators form an anion which only weakly coordinates to a cationic form of the catalyst. Such "ionic cocatalysts" may or may not contain an active proton (e.g. trimethyl ammonium, tributylammonium; N,N-dimethyl anilinium, carbonium, oxonium or sulfonium). They do contain a labile substantially non-coordinating anion (such as tetraphenyl borate or tetrakis(pentafluorophenyl) borate). The preferred of these ionic activators are tris(pentafluorophenyl) borane (which can generate the borate upon reaction with the organometallic catalyst complex), [triphenyl methyl][tetrakis(pentafluorophenyl) borate] and [N,N-dimethyl anilinium][tetrakis(pentafluorophenyl) borate]. In commercial practice, the triphenyl methyl (or "carbonium") salts may be preferred.

These ionic activators are typically used in approximately equimolar amounts (based on the transition metal in the catalyst) but lower levels may also be successful and higher levels also generally work (though suboptimally with respect to the cost-effective use of the expensive activator).

In addition to the catalyst and cocatalyst, the use of a "poison scavenger" may also be desirable. As may be inferred from the name "poison scavenger", these additives may be used in small amounts to scavenge impurities in the polymerization environment. Aluminum alkyls, for example triisobutyl aluminum, are suitable poison scavengers. (Note: some caution must be exercised when using poison scavengers as they may also react with, and deactivate, the catalyst.)

Polymerizations according to this invention may be undertaken in any of the well known olefin polymerization processes including those known as "gas phase", "slurry", "high pressure" and "solution".

The use of a supported catalyst is preferred for gas phase and slurry processes whereas a non-supported catalyst is preferred for the other two.

When utilizing a supported catalyst, it may be preferable to initially support the cocatalyst, then the catalyst (as will be illustrated in the Examples).

20

30

20

30

1

The polymerization process according to this invention uses at least one olefin monomer (such as ethylene, propylene, butene, hexene) and may include other monomers which are copolymerizable therewith (such as other alpha olefins, preferably butene, hexene or octene, and under certain conditions, dienes such as hexadiene isomers, vinyl aromatic monomers such as styrene or cyclic olefin monomers such as norbornene).

It is especially preferred that the polymerization process utilize a major portion of ethylene monomer and a minor portion of an alpha olefin comonomer selected from butene, hexene and octene so as to produce a linear low density polyethylene ("LLDPE") product.

Our experimental data illustrate that organometallic complexes prepared from phospholes according to this invention are excellent polymerization processes. The organometallic complexes having a bridged fluorenyl phospholyl ligand according to this invention display particularly desirable behavior in high temperature ethylene polymerization in that the resulting polyethylene has high molecular weight.

The most preferred polymerization process of this invention encompasses the use of the novel catalysts (together with a cocatalyst) in a medium pressure solution process. As used herein, the term "medium pressure solution process" refers to a polymerization carried out in a solvent for the polymer at an operating temperature from 100 to 320°C (especially from 120 to 220°C) and a total pressure of from 3 to 35 mega Pascals. Hydrogen may be used in this process to control (reduce) molecular weight. Optimal catalyst and cocatalyst concentrations are affected by such variables as temperature and monomer concentration but may be quickly optimized by non-inventive tests.

Further details concerning the medium pressure polymerization process (and the alternative gas phase, slurry and high pressure processes) are well known to those skilled in the art (and widely described in the open and patent literature).

EXAMPLES

The invention will now be illustrated in further detail by way of the following non-limiting examples. For clarity, the Examples have been divided into three parts, namely Part A (Synthetic Methods), Part B (Solution Polymerization), and Part C (Gas Phase Polymerization).

PART A: Synthetic Methods

10

Part A is divided into five sub-sections: Part A1 (Synthesis of a novel phosphole, namely 2-(cyclopentadienyldimethylsilyI)-1-phenyl-3,4,5trimethylphosphole); Part A2 (Synthesis of ansa-[dimethylsilyl(n⁵cyclopentadienyl-3,4,5-trimethylphospholyl] zirconium dichloride - also referred to herein as Me₂Si(Cp)(C₄PMe₃)ZrCl₂); Part A3 (Synthesis of ansa-[dimethylsilyl(η^5 -fluorenyl)(η^5 -3,4,5-trimethylphospholyl)) zirconium dichloride - also referred to herein as Me₂Si(Flu)(C₄PMe₃)ZrCl₂); Part A4 (Synthesis of ansa-{dimethylsilyl(η^5 -fluorenyl)(η^5 -3,4-dimethylphospholyl)) zirconium dichloride - also referred to herein as Me₂Si(Flu)(C₄PHMe₂)ZrCl₂); and Part A5 (Synthesis of 2-dimethyl(2,7-di-

20

tert-butyl-9-fluorenyl)silyl-3,4,5-trimethyl-1-phenylphosphole).

Part A1

Synthesis of 2-(cyclopentadienyldimethylsilyl)-1-phenyl-3,4,5trimethylphosphole):

30

Step 1. Preparation of chlorodimethyl-1-propynylsilane

To a solution of dichlorodimethylsilane (60 milliliters (mL). 495 millimoles (mmol)) in diethyl ether (75 mL) at -20°C was added a tetrahydrofuran (THF) solution of propynylmagnesium bromide (200 mL, 0.5 molar (M), 100 mmol). Addition was completed over 30 minutes and then the reaction was allowed to warm to room temperature. The solvent and excess silane were distilled off at ambient pressure and the residue

20

30

filtered to remove solids. The resulting oil was distilled at ambient pressure and the fraction boiling between 90-120°C was isolated. Redistillation gave pure product. Yield, 4.654 grams (g). Proton nuclear magnetic resonance spectrum (^{1}H NMR) in deuterated toluene ($C_{7}D_{8}$): 1.38 (peak area = 3 protons (3H)), 0.391(6H).

Step 2. Preparation of bis(η5-cyclopentadien-1-yl)(1-chlorodimethylsilyl-2,3,4-trimethyl-1,3-butadienyl-1,4-diyl) zirconium

To a slurry of bis(cyclopentadienyl)zirconium chloride hydride (3.802g, 14.74 mmol) in methylene chloride (50 mL) at 0°C was added 2butyne (2.5 mL, 1.72g, 32 mmol). The reaction was allowed to warm to room temperature and after 30 minutes a clear solution had formed. The solvent and excess butyne were removed in vacuo and the residues dissolved in THF (30 mL). The solution was cooled to -78°C and a solution of methyl lithium in ether (1.4M, 10.5 mL, 15 mmol) was added. After 15 minutes chlorodimethyl-1-propynylsilane (1.955g, 14.7 mmol) was added and the reaction mixture allowed to warm to room temperature. During warming gas evolution was apparent. The reaction was stirred at room temperature for 45 minutes, at 45°C for 2 hours and then at room temperature overnight. The solvent was removed in vacuo and the residues treated with hexane (50 mL). The reaction was filtered and the filtrate concentrated until crystals started to form. The reaction was then stored at -15°C for two days. The mother liquor was cannulated away and the orange crystals dried in vacuo. Yield, 4.2g. ¹H NMR (C₇D₈): 6.01 (10H), 1.78 (3H), 1.65 (3H), 1.53 (3H), 0.50 (6H).

Step 3. Preparation of 2-chlorodimethylsilyl-1-phenyl-3,4,5trimethylphosphole

Bis(η5-cyclopentadien-1-yl)(1-chlorodimethylsilyl-2,3,4-trimethyl-1,3-butadienyl-1,4-diyl) zirconium (2.11g, 5.18 mmol) and phenylphosphine dichloride (0.926g, 5.18 mmol) were combined with toluene (40 mL) and heated to reflux for three hours. The reaction was allowed to cool to room temperature and the solvent was removed in

vacuo. Hexane (50 mL) was added and the reaction mixture cooled to 0°C. Subsequent filtration and removal of the solvent yielded a dark orange oil. This was further purified by a second hexane extraction to remove zirconocene dichloride. Yield, 1.358g. ^{1}H NMR ($C_{7}D_{8}$): 7.27 (multiplet (m), 2H), 7.00 (m, 3H), 2.17 (doublet (d), coupling constant (J) = 4.4 Hz, 3H), 1.81 (d, J = 11.6 Hz, 3 H), 1.66 (3H), 0.46 (3H), 0.41 (3H).

Step 4. Preparation of 2-(cyclopentadienyldimethylsilyl)-1-phenyl-3.4.5-trimethylphosphole

To a solution of 2-chlorodimethylsilyl-1-phenyl-3,4,5-trimethylphosphole (552 mg, 1.87 mmol) in THF (15 mL) at -78°C was added a THF (20 ml) solution of CpLi (136 mg). The solution became cloudy and was allowed to warm to room temperature. The reaction was stirred overnight and then the solvent was removed in vacuo and the product characterized by 1H NMR spectroscopy. The NMR spectrum showed the product was form in high yield with good purity. 1 H NMR (C_7D_8): 7.3, 7.0, 6.7 (broad), 2.07 (d), 1.85 (d), 1.74, 0.12, -0.04. Note:

One might briefly summarize the above described synthesis of "bridged phosphole" structures as involving the crucial steps of (a) reacting the zirconacycle with a phosphine dihalide (Step 3 of Part A1) followed by (b) reacting the phosphole product from (a) with an organometallic cyclopentadienyl reagent (Step 4 of Part A1). It will be appreciated by those skilled in the art that the reverse order of steps (a) and (b) may also be used to access the inventive phospholes from the zirconacycle (i.e. first react the zirconacycle with the organometallic cyclopentadienyl reagent, then react the resulting intermediate with a phosphine dihalide). Similarly, it will be further recognized that the inventive phospholes may also be accessed from the 2-halophosphole via metallation and treatment with a cyclopentadienyl substituted silane which is functionalized with a leaving group (e.g. Cp-SiMe₂Cl). (A discussion of the preparation of a 2-halophosphole is provided in Part A4 below.)

30

20

Part A2

Synthesis of ansa-[dimethylsilyl(η^5 -cyclop ntadi nyl)(η^5 -3,4,5-trimethylphospholyl]zirconium dichloride:

10

20

30

A solution of 2-(cyclopentadienyldimethylsilyl)-1-phenyl-3,4,5trimethylphosphole (1.87 mmol, from the previous experiment) in THF (20 mL) was added to lithium foil (37 mg). After being stirred for 2.5 hours, the dark red solution was added to a solution of trimethyltin chloride (870 mg, 4.37 mmol) in THF (10 mL) at -78°C. The reaction was warmed to room temperature and stirred for one hour. The resulting pale orange solution was then added to ZrCl₄.2THF (705 mg, 1.87 mmol) in THF (10 mL) at -78°C. The reaction was stirred overnight at room temperature before the THF and other volatiles were removed in vacuo and toluene added. The toluene solution was heated to 100°C for 1.5 hours, filtered and the volatiles were removed in vacuo. Pure product was obtained by recrystallizing the resulting residue from toluene and hexane at -30°C. Yield, 138 mg of high purity product plus 369 mg of >90% purity product. ¹H NMR (C₇D₈): 6.79 (1 H), 6.63 (1H), 5.90 (1H), 5.39 (1H), 2.23 (d, J = 10.3 Hz, 3H), 1.97 (3H), 1.71 (3H), 0.54 (3H), 0.29 (3H).

Part A3

Synthesis of ansa-[dimethylsilyl(η^5 -fluorenyl)(η^5 -3,4, 5-trimethylphospholyl)] zirconium dichloride:

Step 1. Preparation of 2-dimethyl(9-fluorenyl)silyl-1-phenyl-3,4,5trimethylphosphole

20

To a solution of 2-chlorodimethylsilyl-1-phenyl-3,4,5-trimethylphosphole (0.496 g, 1.68 mmol) in THF (15 mL) at -78°C was added a THF (15 mL) solution of fluorenyl lithium (0.294 mg, 1.70 mmol). The reaction was warmed to room temperature and stirred for 2 hours. Removal of the solvent gave the product. 1 H NMR (C_7D_8): 7.7 (d), 7.4 (m), 7.2 (m), 6.9 (m), 3.95 (s), 2.02 (d), 1.87 (d), 1.8 (s), 0.12 (s), -0.30 (s). Step 2. Preparation of ansa-[dimethylsilyl(η^5 -fluorenyl)(η^5 -3,4, 5-

trimethylphospholyl)] zirconium dichloride

30

A solution of 2-dimethyl(9-fluorenyl)silyl-1-phenyl-3,4,5-trimethylphosphole (1.65 mmol) in THF (30 mL) was added to lithium foil (33 mg, 4.7 mmol) at room temperature. Over the next two hours the reaction became a deep red color. The solution was cannulated away from the excess lithium and added to a solution of trimethyltin chloride (750 mg, 3.8 mmol) in THF (15 mL) at -78°C. The reaction was allowed to warm to room temperature and it became almost colorless. [A small aliquot of this reaction mixture was taken and examined by ¹H NMR

spectroscopy. The NMR spectrum showed that the distannyl had form essentially quantitatively. ¹H NMR (C₇D₈): 7.85, 7.55, 7.2, 1.95 (d), 1.66 (s), 1.36(s), 0.55 (s), 0.15 (d), -0.11 (s).] The THF and other volatiles were removed in vacuo from the reaction mixture and the residue dissolved in toluene (15 mL). The reaction mixture was then added to a toluene (15 mL) slurry of ZrCl₄ at -78°C. After warming to room temperature the reaction was heated to 100°C for 5 hours and then filtered hot. The residues were washed with hot toluene and the toluene fractions combined. Concentration of the orange toluene solution to 50 mL and cooling to - 15°C overnight gave deep orange crystals of the product. ¹H NMR (C₇D₈): 7.9-7 (m), 2.0 (d, 3H), 1.9 (d, 6 H), 0.92 (3H), 0.88 (3H).


Part A4

Synthesis of ansa-[dimethylsilyl(η^5 -fluorenyl)(η^5 -3,4-dimethylphospholyl)] zirconium dichloride:

20

30

10



Step 1.

2-Bromo-3,4-dimethyl-1-phenylphosphole was prepared according to a literature method (E. Deschamps and F. Mathey, Bull. Soc. Chim. Fr. 1992, 129, 486.).

Step 2. Preparation of 2-chlorodimethylsilyl-3,4-dimethyl-1-phenylphosphole

ⁿBuLi ((1.6 M, 2.33 mL, 3.74 mmol) was added dropwise to a solution of 2-bromo-3,4-dimethyl-1-phenylphosphole (1.0 g, 3.74 mmol) in THF (15 mL) at -105°C. The resultant orange solution was stirred at -100°C for 45 min to ensure complete lithiation. Me₂SiCl₂ (4.82g, 37.4

20

30

mmol) was then added. The solution was stirred for 12 hr while the reaction was warmed to 23°C. The solution was pumped to dryness and the residue was extracted with hexane. The hexane extract was pumped to dryness to give the product as an almost colorless oil in quantitative yield. 1 H NMR (C_7D_8): 0.42 (s, 6H), 2.127(dd, J_1 = 2.91Hz, J_2 = 1.34Hz, 3H), 2.32 (d, J = 4.4 Hz, 3H), 6.75 (d, J = 40 Hz, 1H), 7.2 - 7.4 (m, 5H).

Step 3. Preparation of 2-dimethyl(9-fluorenyl)silyl-3,4-dimethyl-1-phenylphosphole

A solution of 2-chlorodimethylsilyl-3,4-dimethyl-1-phenylphosphole (3.74 mmol) in THF (20 mL) was cooled to -100°C. Fluorenyl lithium (0.643g, 3.74 mmol) in THF(20 mL) was then added. The resultant mixture was stirred for 4 hr while it warmed to 23°C and then it was heated to 50°C for 20 min. The solution was pumped to dryness and the residue was dissolved in toluene (10 mL). The toluene solution was passed through a short column of neutral alumina (Brockman activity 1). The column was thoroughly rinsed with toluene to ensure all the desired product was freed from the column. The combined filtrate was pumped to dryness to give the product. Yield 1.435 g, 3.495 mmol, 94%. 1 H NMR (C_7D_8): -0.3 (br. s, 3H), 0.15 (br. s, 3H), 1.95 (dd, J_1 = 3.0 Hz, J_2 = 1.4Hz, 3H), 2.01 (dd, J_1 = 4.5 Hz, J_2 = 1.0 Hz, 3H), 3.93 (s, 1H), 6.70 (d, J = 41 Hz, 1H), 6.9 - 7.8 (m, 13H).

Step 4. Preparation of ansa-[dimethylsilyl(η⁵-fluorenyl)(η⁵-3,4dimethylphospholyl)]zirconium dichloride

2-dimethyl(9-fluorenyl)silyl-3,4-dimethyl-1-phenylphosphole (0.717 g, 1.747 mmol) in THF (30 mL) was added to lithium foil (~ 100 mg) at

room temperature and the mixture was stirred for 3 hr. An orange solution formed. The solution was separated from the excess of lithium and was treated with a THF solution (20 mL) of Me₃SnCl (0.696 g, 3.50 mmol) at 100°C. A colorless solution formed. The solution was warmed up to 23°C and pumped to dryness. The residue was redissolved in toluene (10 mL) and the slurry pumped to dryness to remove trace amounts of THF. Toluene (10 mL) was added to the flask again to dissolve the residue and the slurry was filtered into a slurry of ZrCl4 (0.659g, 1.747 mmol) in toluene (10 mL). A reddish orange solution formed after the addition. The solution was warmed to 100°C for 3 hr and then pumped to dryness. The product was isolated by recrystallization of the residue from ether.

¹H NMR (C₇D₈, d): 0.827(s, 3H), 0.907 (d, J = 0.95 Hz, 3H), 1.848 (s, 3H), 1.988 (s, 3H), 6.67 (d, J = 38 Hz, 1H), 7.1 - 7.9 (m, 8H).

Part A5

10

Synthesis of 2-dimethyl(2,7-di-tert-butyl-9-fluorenyl)silyl-3,4,5trimethyl-1-phenylphosphole:

30 Step 1.

2,7-di-tert-butyl-fluorenyl lithium (1.6 mmol) was prepared by reacting 2,7-di-tert-butyl-fluorene (1.6 mmol, 0.445) and ⁿBuLi (1.6 mol) in diethyl ether at 23°C for 2 hours.

Step 2.

The title compound was prepared by reacting 2,7-di-tert-butyl-fluorenyl lithium (1.6 mmol, from Step 1 above) with 2-chlorodimethylsilyl-1-phenyl-3,4,5 trimethylphosphole (1.6 mmol, 0.472 g) using the

FU I/UNDO/UNALO

procedures previously described in Parts A1 and A4. 1H NMR (C_7D_8): - 0.30(br.s), 0.38 (br.s), 1.36(s), 1.37 (s), 1.90(d), 1.94 (d), 2.03 (d), 3.96 (s), 6.9 -7.8 (m).

PART B: Solution Polymerization

Part B illustrates the (co)-polymerization of ethylene under solution polymerization conditions. Part B1 describes continuous flow solution polymerizations. Part B2 describes batch solution polymerizations. Inventive polymerizations using "bridged phospholes" are polymerizations done with prior art, unbridged phospholes and to metallocenes. The data clearly illustrate that the inventive systems provide excellent polymerization rates. In addition, the dimethyl silyl bridged phosphole-fluorenyl complexes provide high molecular weight polymers under high temperature polymerization conditions.

Part B1

Continuous Solution Polymerization

20

10

All the polymerization experiments described below were conducted on a continuous solution polymerization reactor. The process is continuous in all feed streams (solvent, monomers and catalyst) and in the removal of product. All feed streams were purified prior to the reactor by contact with various absorption media. All components were stored and manipulated under an atmosphere of purified nitrogen.

All the examples below were conducted in a reactor of 71.5 cubic centimeters (cc) internal volume. In each experiment the volumetric feed to the reactor was kept constant and as a consequence so was the reactor residence time.

30

The catalyst solutions were pumped to the reactor independently and there was no pre-contact between the activator and the catalyst. Because of the low solubility of the catalyst and the MAO in cyclohexane, solutions were prepared in toluene. The catalyst was activated *in situ* (in the polymerization reactor) at the reaction temperature in the presence of the monomers. The polymerizations were carried out in cyclohexane at a pressure of 1500 pounds per square inch (psi). Ethylene was supplied to

the reactor by a calibrated thermal mass flow meter and was dissolved in the reaction solvent prior to the polymerization reactor. If comonomer was used it was also premixed with the ethylene before entering the polymerization reactor. Under these conditions the ethylene conversion is a dependent variable controlled by the catalyst concentration, reaction temperature and catalyst activity etc.

10

The internal reactor temperature is monitored by a thermocouple in the polymerization medium and can be controlled at the required set point to +/- 0.5°C. Downstream of the reactor the pressure was reduced from the reaction pressure (1500 psi) to atmospheric. The solid polymer was then recovered as a slurry in the condensed solvent and was dried by evaporation before analysis.

The ethylene conversion was determined by a dedicated on line gas chromatograph.

Polymer Analysis

20

Gel permeation chromatography ("GPC") analysis was carried out on a Waters 150C GPC using 1,2,4-trichlorobenzene as the mobile phase at 140°C. The samples were prepared by dissolving the polymer in the mobile phase solvent in an external oven at 0.1% (weight/volume) and were run without filtration. Molecular weights are expressed as polyethylene equivalents with a relative standard deviation of 2.9% and 5.0% for the number average molecular weight (Mn) and weight average molecular weight (Mw), respectively.

30

Melt index (MI) measurements were conducted according to ASTM method D-1238-82.

Polymer densities were measured on pressed plaques (ASTM D-1928-90) with a densitometer.

Example B1

 $Me_2Si(Cp)(C_4PMe_3)ZrCl_2$ was added to the reactor at 37 x 10^{-6} mol/l along with PMAO-IP (Akzo-Nobel) at Al/Ti = 200 (mol/mol). The reaction temperature was $160^{\circ}C$ and 1 gram/min (g/min) of ethylene was

continuously added to the reactor. An ethylene conversion of 86.4% was observed (see table 1).

Example B2

Conditions were as in example B1 except that 2.1 g/min of ethylene was added to the reactor. An ethylene conversion of 87.9% was seen (see table 1).

Example B3

10

20

30

Conditions were as in example B1 except that 2.1 g/min of ethylene and 3 ml/min of 1-octene was added to the reactor. An ethylene conversion of 87.2% was seen (see table 1).

Comparative Example B4-C

This comparative example uses an unbridged cyclopentadienyl-phospholyl complex. Thus, $(\eta^5$ -cyclopentadienyl) $(\eta^5$ -2,3,4,5-tetramethylphospholyl) zirconium dichloride (°(Cp)(C₄PMe₄)ZrCl₂") was added to the reactor at 37 x 10⁻⁶ mol/l along with MMAO-3 (Akzo-Nobel) at Al/Ti = 400 (mol/mol). The reaction temperature was 160°C and 1 gram/min of ethylene was continuously added to the reactor. An ethylene conversion of 68.3% was observed (see table 2).

Comparative Example B5-C

This comparative example also uses the unbridged complex $(Cp)(C_4PMe_4)ZrCl_2$. Thus, $(Cp)(C_4PMe_4)ZrCl_2$ was added to the reactor at 37 x 10⁻⁶ mol/l along with MMAO-3 (Akzo-Nobel) at Al/Ti = 400 (mol/mol). The reaction temperature was 160°C and 2.1 gram/min of ethylene was continuously added to the reactor. An ethylene conversion of 79.3% was observed (see table 2).

Comparative Example B6-C

 $(Cp)(C_4PMe_4)ZrCl_2$ was added to the reactor at 37 x 10⁻⁶ mol/l along with MMAO-3 (Akzo-Nobel) at Al/Ti = 400 (mol/mol). The reaction temperature was 160°C and 2.1 gram/min of ethylene and 3.25 ml/min of 1-octene was continuously added to the reactor. An ethylene conversion of 81.0% was observed (see table 2).

20

30

Comparative Example B7-C

This comparative example employs a metallocene catalyst (i.e. no phospholyl ligand). Thus, $(C_5Me_5)_2ZrCl_2$ was added to the reactor at 37 x 10^{-6} mol/l along with MMAO-3 (Akzo-Nobel) at Al/Ti = 400 (mol/mol). The reaction temperature was 160°C and 1 gram/min of ethylene was continuously added to the reactor. An ethylene conversion of 35.6% was observed (see table 2).

Comparative Example B8-C

 $(C_5Me_5)_2ZrCl_2$ was added to the reactor at 37 x 10⁻⁶ mol/l along with MMAO-3 (Akzo-Nobel) at Al/Ti = 400 (mol/mol). The reaction temperature was 160°C and 2.1 gram/min of ethylene was continuously added to the reactor. An ethylene conversion of 37.4% was observed (see table 2).

Comparative Example B9-C

 $(C_5\text{Me}_5)_2\text{ZrCl}_2$ was added to the reactor at 37 x 10⁻⁶ mol/l along with MMAO-3 (Akzo-Nobel) at Al/Ti = 400 (mol/mol). The reaction temperature was 160°C and 2.1 gram/min of ethylene and 3.25 ml/min of 1-octene was continuously added to the reactor. An ethylene conversion of 38.5% was observed (see table 2).

Comparative Example B10-C

 $(C_4 PMe_4)_2 ZrCl_2$ was added to the reactor at 37 x 10⁻⁶ mol/l along with MMAO-3 (Akzo-Nobel) at Al/Ti = 400 (mol/mol). The reaction temperature was 160°C and 1 gram/min of ethylene was continuously added to the reactor. An ethylene conversion of 36.6% was observed (see table 2).

		Polymer Melt Index		•	0077	001
10		Polymer Density (g/cc)			₹0.04	
20	TABLE 1	Calculated Polymerization Rate (Vmmol X min)	64.0	04.3	73.8	69.7
20		Ethylene Conversion (%)	86.4		/3.8	87.2
		Total Flow Catalyst To Reactor Concentration (mol x 10 ⁶)	37.0	27.0	37.0	37.0
30		Example Total Flow To Reactor (ml/min)	27.0	27.0	5, ,,,	27.0
		Example	91	B2		83

Θ
ā
Examp
ă
×
W
ø
>
Ξ
50
parative
ŏ
E
0
2 (C
\sim
TABLE
긒
9
٩
_

	_							
Example		Catalyst			Polymer	Polymer	Polymor	L
	To Reactor	Concentration			Mn x 10 ⁻³	May x 10.3	Donition	
	(ml/min)	(mol × 10 ⁶)	(%)	(Vmmol X min)	3		(a/cc)	lialei Ludex
ر <u>۲</u> ۵	010	ļ						
2	0./2		68.3	22.0	7.8	21		
85-C	27.0	37.0	79.3	30.1	7.0	355		
0 90	010	l			0.,	63.8	•	155
2-00	27.0		81.0	43.5	6.7	Ç	000	
87-C	27.0	37.0	25.6	20 11		5	0.363	,
0 00		1	5.50	0.0	20.	7.5		•
2-89	27.0		37.4	6.1	2.2	Ş	1000	
R9.0	27.0	l	1 00		5:5	16	0.987	920
	5,13		38.5	6.4	0.	0		
ק ר	27.0	0.10			2	0.0	•	
ָ כ	2.73		3	- C				

Part B2

Solution Batch Reactor Polymerizations

Anhydrous toluene was purchased from Aldrich and used without further purification. The catalysts Me₂Si(Flu)(C₄PMe₃)ZrCl₂ (1) and Me₂Si(Flu)(C₄PHMe₂)ZrCl₂ (2) used in this study were synthesized as described in Part A above and were used without further purification. Catalyst 1 was dissolved in toluene at 50°C with the help of an ultrasound bath. Catalyst 2 was dissolved in toluene at room temperature. The catalyst concentrations were between 6-7 mg/mL. A portion of this solution was then injected into the reactor to give the required reactor catalyst concentration. A comparative experiment was also completed with a known metallocene having a dimethyl silyl bridge between a cyclopentadienyl group and a fluorenyl group.

A solution semi-batch reactor (SBR) was used in the polymerization experiments. The SBR uses a programmable logical control (PLC) system with commercially available software (Wonderware 5.1) for process control. Ethylene (99.5%, polymer grade, Matheson) and cyclohexane was purified by absorption before use. MAO (MMAO-3 or PMAO-IP) was purchased from Akzo-Nobel. Ethylene polymerizations were performed in a 500 mL Autoclave Engineers Zipperclave reactor equipped with an air driven stirrer and an automatic temperature control system. The experiments were carried out as follows:

30

20

	·
Cyclohexane	228 mL
Catalyst Concentration	53 or 65 μmol/L
Cocatalyst	MAO (MMAO-3 or PMAO-IP; Al/Zr = 300 or 400 mol/mol)
Reaction Temperature	160°C
Reactor Pressure	140 psig total
Stirring Speed	2000 rpm

The polymerization time was 10 min in each experiment. The reaction was terminated by adding 5 mL of methanol to the reactor and the polymer was recovered by evaporation of the cyclohexane.

Polymer molecular weights and molecular weight distributions were measured by GPC (Waters 150-C) at 140°C in 1,2,4-trichlorobenzene calibrated using polyethylene standards.

10

20

TABLE 1A (Polymerization Activity)

xample	Catalyst	Cocatalyst	Al/Zr (mol/mol)	Catalyst Concentration Polymerization Activity g PE/m Molcat*hr1	Polymerization Activity g PE/m Molcat*hr1
	Me ₂ Si(Flu)(C ₄ Pme ₃)ZrCl ₂ PMAO-IP	PMAO-IP	300	53 umol/l	2882
	0 10 10 0/11/10 01V			200111	2002.1
	MB2SI(FID)(CAPHIMB2)ZrCI2 PMAO-IP	PMAO-IP	300		10100
() ()	1(מס איווסייר	4.61.37
ڔ	SIPU2CPFIU2rCI2	MMAO-3	400	65 umol/l	11/8 8
					0.02

1. The calculation of polymerization activity is based on the ethylene uptake.

TABLE 2A (Polymer Properties)

Example	Catalyst	Cocatalyst	Al/Zr (mol/mol)	Catalyst Concentration Mw(*10 ⁻³) Mw/Mn	Mw(*10 ⁻³)	Mw/Mn
0						
20	Me2Si(Flu)(C4Pme3)ZrCi2 PMAO-IP	PMAO-IP	300	53 umol/l	73	0 7
7			ł		2	
מַע	I Mezul(Flu)(Carimos)ZrCla PMAO-IP	PMAO-IP	300	65 umol/1	22	0 0
0,0	i			30 MINO!! L	5	ر د د
ا ا ا	SIPPSCPFIUARCI2	MMAO-3	400	65 umol/l	21	0 0
						,

The inventive experiments using the "bridged fluorenyl phosphole" complexes (i.e. examples B11 and B12) are different from the comparative experiment using the "bridged fluorenyl cyclopentadienyl" complex in the following respects:

(a) the inventive polymerizations were more active;

the polymers produced by the inventive experiments have higher molecular weight (which is very desirable for <u>B</u>

high temperature polymerizations); and the polymer from the comparative experiment has a narrower molecular weight distribution.

j

10

PART C: Gas Phase Polymerization

This section illustrates gas phase polymerization according to the present invention and also provides comparative examples.

Example C1:

Use of Me₂Si(Cp)(C₄PMe₃)ZrCl₂

Preparation of Supported Catalyst

Commercial MAO on granular silica (1.23 g, Witco TA 02794/HL/04, 23 wt % Al) was suspended in anhydrous toluene (40 mL). A solution of Me₂Si(Cp)(C₄PMe₃)ZrCl₂ was prepared in anhydrous toluene (0.012 mol/L) and a volume of 10 mL of this solution was added dropwise to a stirred suspension of the MAO on silica. The mixture was allowed to stir overnight and subsequently heated at 45°C for a period of 2.5 hours. The resulting solid was collected via filtration and washed first with toluene (2 x 15 mL) and then hexane (2 x 20 mL). After drying in vacuo, 1.13 grams of a free-flowing powder was obtained. Polymerization

20

30

10

Gas phase ethylene homopolymerization of the supported catalyst was conducted by introducing the catalyst (23 mg) into a continuously stirred, 2L pressure vessel under operating conditions of 200 psig ethylene (Praxair, polymerization grade) and at a constant temperature of 90°C for a period of 1 hr. A seed bed of NaCl (70 g, oven dried at 175°C for 48 hours), treated *in situ* with a heptane solution of triisobutylaluminum (TIBAI, 1 mL of a 25 wt % solution, Akzo Nobel), was added to the reactor prior to introduction of the catalyst. Upon termination of the reaction and isolation of the polymer, a free-flowing product was obtained in a yield of 41 g, representing a catalyst activity of 198,000 g PE/g Zr x hr. The polymer, characterized by gel permeation chromatography (GPC), showed a molecular weight of 89,000 (Mw) and a polydispersity of 2.2.

20

30

Example C2: Ethylene - 1-butene copolymerization using silica supported Me₂Si(Cp)(C₄PMe₃)ZrCl₂

Polymerization

Gas phase ethylene - 1-butene copolymerization of the supported catalyst described in Example C1 was conducted by introducing the catalyst (23 mg) into a continuously stirred, 2L pressure vessel under operating conditions of 200 psig of a continuously supplied four mol % mixture of 1-butene in ethylene (Airgas, polymerization grade) and at a constant temperature of 90°C for a period of 1 hr. A seed bed of NaCl (70 g, oven dried at 175°C for 48 hours), treated *in situ* with a heptane solution of tri-isobutylaluminum (TIBAI, 1 mL of a 25 wt % solution, Akzo Nobel), was added to the reactor prior to introduction of the catalyst. Upon termination of the reaction and isolation of the polymer, a free-flowing product was obtained in a yield of 39 g, representing a catalyst productivity of 185,000 g PE/g Zr x hr. The polymer, characterized by gel permeation chromatography (GPC), showed a molecular weight of 111,000 (Mw) and a polydispersity of 3.5.

Example C3: Ethylene polymerization using silica supported Me₂Si(Flu)(C₄PMe₃)ZrCl₂

Catalyst Synthesis

Commercial MAO on granular silica (0.45 g, Witco TA 02794/HL/04, 23 wt % Al) was suspended in anhydrous toluene (10 mL). A solution of Me₂Si(Flu)(C₄PMe₃)ZrCl₂ was prepared in anhydrous toluene (0.00064 mol/L) and a volume of 69 mL of this solution was added dropwise to a stirred suspension of the MAO on silica. The mixture was allowed to stir overnight. The resulting solid was collected via filtration and washed first with toluene (2 x 15 mL) and then hexane (2 x 20 mL). After drying in vacuo for 1 hour, a free-flowing powder was obtained.

Polymerization

Gas phase ethylene homopolymerization of the supported catalyst was conducted by introducing the catalyst (18 mg) into a continuously

stirred, 2L pressure vessel under operating conditions of 200 psig ethylene (Praxair, polymerization grade) and at a constant temperature of 90°C for a period of 1 hr. A seed bed of NaCl (70 g, oven dried at 175°C for 48 hours), treated *in situ* with a heptane solution of triisobutylaluminum (TIBAI, 1 mL of a 25 wt % solution, Akzo Nobel), was added to the reactor prior to introduction of the catalyst. Upon termination of the reaction and isolation of the polymer, a free-flowing product was obtained in a yield of 15 g, representing a catalyst productivity of 97,000 g PE/g Zr x hr.

10

20

Comparative Example C4-C: Preparation and ethylene polymerization of silica supported bistetramethylphospholyl zirconium dichloride

Catalyst Preparation

The same procedure as described in Example C1 was used, except that an unbridged bis phospholyl, namely bis-tetramethylphospholyl zirconium dichloride (25 mL having a concentration of 0.016 mol/L), was used. 1.7 g of catalyst was obtained.

Polymerization

Using the same procedure as described in Example C1, 4.7 g of polyethylene was obtained, representing a catalyst productivity of 20,600 g/g Zr x hr. The polymer, characterized by gel permeation chromatography (GPC), showed a molecular weight of 226,000 (Mw) and a polydispersity of 4.9.

30

Comparative Example C2-C: Preparation and ethylene polymerization of silica supported tetramethylphospholyl(cyclopentadienyl) zirconium-dichloride

Catalyst Preparation

The same procedure as described in Example C1 was used, except that Tetramethylphospholyl(cyclopentadienyl) zirconium dichloride (35 mL

having a concentration of 0.017 mol/L) was used. 2.8 g of the MAO on silica was used. 2.7 g of catalyst was obtained.

Polymerization

Using the same procedure as described in Example C1, 4.8 g of polyethylene was obtained, representing a catalyst productivity of 20,800 g/g Zr x hr. The polymer, characterized by gel permeation chromatography (GPC), showed a molecular weight of 209,000 (Mw) and a polydispersity of 6.9.

INDUSTRIAL APPLICABILITY

This invention provides an efficient synthetic method for the preparation of compounds which are useful in the manufacture of catalysts for olefin polymerization.

20

CLAIMS

1. A phosphole characterized by having at least two substituents (a) and (b) where substituent (a) is a leaving group bonded to the phosphorus atom in the phosphole ring and substituent (b) is bonded to one carbon atom in the phosphole ring and is defined by the formula:

wherein Cp* is selected from cyclopentadienyl; substituted cyclopentadienyl; indenyl; substituted indenyl; fluorenyl and substituted fluorenyl; each SI is a non-interfering spectator ligand; Y is a metalloid bridging atom selected from Si, Ge, Sn, N, P, B and AI; and Z is one, two or three depending upon the valence of atom Y.

- 2. A phosphole according to claim 1 wherein each SI is independently selected from hydrogen, halogen and a hydrocarbyl having from 1 to 15 carbon atoms.
- 3. A phosphole according to claim 1 and defined by the formula:

30

10

20

wherein:

 $R_{1},\ R_{2},\ and\ R_{3},\ are\ hydrogen\ or\ non-interfering\ substituents;$

L is a leaving group;

Cp* and SI are as defined in claim 1; and

Y is selected from Si, Ge and Sn.

20

- 4. A phosphole according to claim 3 wherein said non-interfering substituents are each, independently selected from hydrogen, alkyls having from 1 to 20 carbon atoms and aryls having 1 to 20 carbon atoms and said leaving group is selected from hydrogen, aryls, trialkyl Si, trialkyl tin and halogen.
- 5. A phosphole according to claim 1 selected from 2-dimethyl(2,7,-ditert-butyl-9-fluorenyl)silyl-3,4,5-trimethyl-1-phenylphosphole and 2-(cyclopentadienyldimethylsilyl)-1-phenyl-3,4,5-trimethylphosphole.
- 6. A process to prepare a phosphole according to claim 3 wherein said process comprises the reaction of a reactive organometallic cyclopentadienyl reagent with a bifunctional phosphole defined by the formula:

wherein:

R₁, R₂, R₃, Y, SI, and L are as defined in claim 3;

Z is 2; and


Hal is selected from halogen and pseudohalogen.

- 7. The process according to claim 6 wherein Hal is selected from CI, Br, I and OR¹ wherein R¹ is a hydrocarbyl having from 1 to 20 carbon atoms.
- 8. The process according to claim 6 wherein said reactive organometallic cyclopentadienyl reagent is defined by the formula:

Cp* M

wherein Cp* is selected from cyclopentadienyl; substituted cyclopentadienyl; indenyl; substituted indenyl; fluorenyl and substituted fluorenyl; and M is selected from group 1 metals, group 2 metals, Al and Ti.

- 9. The process according to claim 8 wherein M is selected from Li, K, and Mg.
- 10. A process to prepare a group 4 organometallic complex comprising the reaction of a phosphole according to claim 1 with a metal compound which contains a metal selected from Ti, Hf and Zr.
 - 11. A process according to claim 10 wherein said group 4 organometallic complex is defined by the formula:



20

30

wherein:

each SI is a non-interfering spectator ligand;

Y is selected from Si, Ge and Sn;

Z is 2;

 R_1 , R_2 , and R_3 are hydrogen or non-interfering substituents; Cp^* is selected from cyclopentadienyl, substituted cyclopentadienyl, indenyl, substituted indenyl, fluorenyl and substituted fluorenyl; M4 is selected from Ti, Zr and Hf;

X is an anionic ligand; and

n is 1 or 2, depending upon the oxidation state of M4.

12. The process according to claim 10 wherein said metal compound is a four valent metal halide selected of the formula:

(M4)H₄

wherein M4 is as defined in claim 10; and H is selected from chlorine and bromine.

- 13. A process for polymerizing at least one polymerizable alpha olefin comprising reacting a cocatalyst and a group 4 organometallic complex prepared according to claim 9 with said at least one alpha olefin.
- 14. The process according to claim 13 wherein said cocatalyst is an alumoxane.
- 15. The process according to claim 13 wherein said cocatalyst is an ionic activator.
- 16. The process according to claim 13 wherein said at least one polymerizable alpha olefin comprises a majority of ethylene and a minor portion of at least one of propylene, butene-1, pentene-1, hexene-1, and octene-1.
- 17. The process according to claim 13 when conducted in a gas phase polymerization reactor.
- 20 18. A process for the polymerization of at least one olefin comprising reacting at least one alpha olefin monomer under polymerization conditions with a cocatalyst and a group 4 organometallic complex of the formula:

30

10

wherein:

Flu* is selected from fluorenyl and substituted fluorenyl; each SI is a non-interfering spectator ligand;


Y is selected from Si, Ge, and Sn;

 R_1 , R_2 , and R_3 are hydrogen or non-interfering substituents; M4 is selected from Ti, Zr and Hf;

20

X is an anionic ligand; and n is 1 or 2 depending upon the oxidation state of M4.

- 19. The process according to claim 18 wherein said cocatalyst is an ionic activator.
- 20. The process according to claim 18 wherein said at least one alpha olefin comprises a majority of ethylene and a minor portion of at least one of propylene, butene-1, pentene-1, hexene-1 and octene-1.
- 21. The process according to claim 18 when conducted at a temperature of from 120°C to 300°C.
- 22. The process according to claim 18 when conducted in the presence of a solvent for the polymer produced by the process.
- 23. A medium pressure solution polymerization process comprising reacting an activator and a group 4 metal complex having a bridged fluorenyl phospholyl ligand with at least one polymerizable alpha olefin at a temperature of from 140°C to 300°C at a pressure of from 4 to 20 mega Pascals in a solvent for polymer produced by the process.
- 24. The process according to claim 23 wherein said cocatalyst is an ionic activator.
- 25. The process according to claim 24 wherein said ionic activator is provided as a carbonium salt of a substantially non-coordinating anion.
- 26. The process according to claim 23 wherein said group 4 metal complex is defined by the formula:



wherein:

Flu* is selected from fluorenyl and substituted fluorenyl; each SI is a non-interfering spectator ligand;

Y is selected from Si, Ge, and Sn;

R₁, R₂, and R₃ are hydrogen or non-interfering substituents;

M4 is selected from Ti, Zr and Hf;

X is an anionic ligand; and

n is 1 or 2 depending upon the oxidation state of M4.

INTERNATIONAL SEARCH REPORT

PCT/CA 98/00428

A C: 45	CIEICA TION OF CUID IT OF THE		
ÎPC 6	SSERCATION OF SUBJECT MATTER C07F9/6568 C07F17/00 C08F1	0/00	
According	g to International Patent Classification (IPC) or to both national da	reification on a IDC	,
	DS SEARCHED	SSICEROII BIED IF C	
Minimum	documentation searched (classification system followed by classification system)	lication symbols)	
IPC 6	C07F C08F		
Document	tation searched other than minimum documentation to the extent L	nol such documents are locky	act in the Golds securities
	·		
Electronic	data base consulted during the international search (name of dal	a base and, where practical, e	earch lerms used)
C. DOCUM	MENTS CONSIDERED TO BE RELEVANT		
Category *	Cliation of document, with indication, where appropriate, of the	relevant passages	Relevant to claim No.
A	WO 95 04087 A (SHELL CANADA LTI).) 9	1-26
	February 1995 cited in the application		
	see the whole document		
A	US C 153 157 4 (005000)		
n	US 5 153 157 A (GREGORY G. HLAT October 1992	KY) 6	1-26
	cited in the application		
	see the whole document		
	-		
Furth	er documents we licted in the continuation of box C.	X Patent family men	ibers are tisted in armex.
Special cate	egories of cited documents;		· · · · · · · · · · · · · · · · · · ·
	defining the general state of the art which is not	"I fater document published or priority date and no	ed after the International filling date. I in conflict with the application but
CONSIDE	red to be of particular relevance ocument but published on or after the International	clied to understand the invention	principle or theory underlying the
nang ua	IB.	"X" document of particular cannol be considered	relevance; the claimed invention novel or cannot be considered to
MIDCH IS	if which may throw doubts on priority claim(s) or cited to establish the publication date of another or other special reason (as specified)	involve an inventive st	ep when the document is taken alone selvance; the claimed Invention
	it referring to an oral disclosure, use, exhibition or	cannot be considered document is combined	to involve an inventive step when the with one or more other such docu-
P* documen	t published prior to the international filling date but	ments, such combinati in the art.	on being obvious to a person skilled
Gier trial	ine priority date craimed	"&" document member of th	
	trual completion of their international search	Date of mailing of the in	ternational search report
	August 1998	11/08/199	
ame and me	iting address of the ISA European Palent Office, P.B. 5818 Patentinan 2	Authorized officer	
	NL - 2280 HV Hijswijk Tel. (+31-70) 340-2040, Tx, 31 651 epo nl.		
	Fax: (+31-70) 340-3016	Beslier, t	•

		Т	.		98/00428
Patent document cited in search report		Publication date		Patent family member(s)	Publication date
WO 9504087	A	09-02-1995	EP	0638593 A	15-02-1995
			US	5756417 A	26-05-1998
			, AT	160790 T	15-12-1997
			UA	682395 B	02-10-1997
			UA	7610394 A	28-02-1995
			BR	9407165 A	17-09-1996
			CA	2168564 A	09-02-1995
			CN	1128539 A	07-08-1996
			DE	69407192 D	15-01-1998
			DE	69407192 T	26-03-1998
			DK	717754 T	23-02-1998
			EΡ	0717754 A	26-06-1996
			ES	2110257 T	01-02-1998
			JP	8510006 T	22-10-1996
US 5153157	A	06-10-1992	CA	2078665 A	21-09-1991
			DE	69120667 D	08-08-1996
			DE	69120667 T	28-11-1996
			EP	0521908 A	13-01-1993
			ES	2089201 T	01-10-1996
		•	MO	9114713 A	03-10-1991
			US	5241025 A	31-08-1993
			AŢ	145218 T	15-11-1996
•			AT	145211 T	15-11-1996
			AU	617990 B	12-12-1991
			AU	1245288 A	24-08-1988
			CA	1339142 A	29-07-1997
			CA CZ	1337142 A 8800579 A	26-09-1995
			DE	3855666 D	15-02-1995
			DE	3855668 D	19-12-1996 19-12-1996
			DK	548888 A	30-11-1988
			EP	0277004 A	03-08-1988
			EP	0468537 A	29-01-1992
			EP	0561479 A	22-09-1993
			ĒΡ	0558158 A	01-09-1993
			ES	2094174 T	16-01-1997
			ES	2094461 T	16-01-1997
:			FI	884487 A	29-09-1988
			HU	211065 B	30-10-1995

MICKINATIONAL DEARCH ALLON

Information on potent family members

PCT/CA 98/00428

Patent document cited in search report	t	Publication date		Patent family member(s)	Publication date
US 5153157	A		JP	8034809 A	06-02-1996
		•	JP	8034810 A	06-02-1996
•			JP	1502036 T	13-07-1989
			KR	9615192 B	01-11-1996
			NO	179589 B	29-07-1996
			RU	2062649 C	27-06-1996
			US	5384299 A	24-01-1995
		•	· US	5391629 A	21-02-1995
			US	5408017 A	18-04-1995
		•	WO	8805793 A	11-08-1988
			US	5621126 A	15-04-1997
			US	5470927 A	28-11-1995
			US	5599761 A	04-02-1997
			US	5198401 A	30-03-1993

Form PCT/ISA/210 (perent family ennes) (July 1992)

---- 2 --- 1